

## FWGPP60-W58ORD

### Face Material

weight	thickness	material
45 g / m <sup>2</sup> ± 10% ISO536	0.06mm ± 10% ISO534	Milky white polypropylene film with pearl luster effect of special coating on the surface

### Liner

58 g / m <sup>2</sup> ± 10% ISO536	0.055mm ± 10% ISO534	white glassine paper with super calender treatment
------------------------------------	----------------------	--

### Adhesive

ORD is a removable adhesive. It has proper initial viscosity and high resilience. It has good final removability and viscosity. It can be torn and pasted on many non-paper stickers without leaving residual glue. The normal use range is wide.

### Peel adhesion

initial adhesion 7 N/25mm or tear off FTM9	20 mins Peel adhesion value on steel at 180 angle 8 N/25mm or tear off FTM1	20 mins Peel adhesion value on steel at 90 angle 5.5N/25mm or tear off FTM2
---	---	---

### Temperature

Min. Appl. Temp. 0 °C	Service Temp. -30°C +80°C (24H after labeling)
-----------------------	--

### Applications

The material has certain tear resistance and chemical corrosion resistance, and is widely used in washing, cosmetics, daily chemicals, kitchen appliances, books and electronic labels and other industries.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

### Printing Methods

White high-gloss polypropylene film with pearl luster effect, with a layer of coating on the surface, can be used for flexographic printing, letterpress printing, screen printing, heat transfer printing and other printing methods, and has good performance on ink. Product labels with important properties such as water resistance, oil resistance and chemicals have good covering performance. Sharp knives shall be used in die cutting, and label overflow caused by too tight winding tension shall be avoided .

### Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.