

PWP70-WP83ER

Face Material

weight	thickness	material
70 g / m ² ± 10% ISO536	0.09mm ± 10% ISO534	Uncoated white matte paper

Liner

80 g / m ² ± 10% ISO536	0.8mm ± 10% ISO534	Monochrome coated white CCK release paper
------------------------------------	--------------------	---

Adhesive

ER is an acrylic adhesive with weak viscosity and is not suitable for repeated pasting. It is not suitable for pasting PE or PVC products, and it is not recommended to apply it to the surface with oil.

Peel adhesion

initial adhesion 5 N/25mm or tear off FTM9	20 mins Peel adhesion value on steel at 180 angle 3.5 N/25mm or tear off FTM1	20 mins Peel adhesion value on steel at 90 angle 3N/25mm or tear off FTM2
---	---	---

Temperature

Min. Appl. Temp. 10 °C	Service Temp. 0 °C +90°C (24H after labeling)
------------------------	---

Applications

This product has good adhesion performance and is widely used in price tags, book labels, computer printed labels and matt labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The surface material has excellent ink absorption and is suitable for a variety of printing methods, including laser and inkjet printing. Matte paper with rough surface is suitable for printing and printing simple pictures and texts. It is applied to office, logistics and other industries.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.